

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 88303919.0

(51) Int. Cl.⁵ C08G 61/08, C08F 210/02,
C08L 23/08, C08L 65/00

(22) Date of filing: 29.04.88

(30) Priority: 01.05.87 JP 106354/87
08.05.87 JP 110630/87

(43) Date of publication of application:
17.11.88 Bulletin 88/46

(64) Designated Contracting States:
AT BE CH DE ES FR GB GR IT LI LU NL SE

(68) Date of deferred publication of the search report:
11.07.90 Bulletin 90/28

(71) Applicant: MITSUI PETROCHEMICAL
INDUSTRIES, LTD.
2-5, Kasumigaseki 3-chome Chiyoda-ku
Tokyo 100(JP)

(72) Inventor: Minami, Syuji
2-2 Misono 1-chome
Ootake-shi Hiroshima(JP)
Inventor: Kawamoto, Keiji
30-6 Ajina 4-chome
Hatsukaichi-shi Hiroshima(JP)
Inventor: Todo, Akira
5 Yushudainishi 2-chome
Ichihara-shi Chiba(JP)
Inventor: Kuroiwa, Toshiaki
4-2 Wakicho, waki 2-chome
Kuga-gun Yamaguchi(JP)
Inventor: Kasai, Tetsuzi
4-3 Wakicho, Waki 2-chome
Kuga-gun Yamaguchi(JP)

(74) Representative: Myerscough, Phillip Boyd et al
J.A.Kemp & Co. 14, South Square Gray's Inn
London, WC1R 5EU(GB)

(54) Cycloolefin type random copolymer compositions and uses thereof.

EP 0 291 208 A3
 (57) Compositions comprising (A) cycloolefin random copolymer containing an ethylene component, and a cycloolefin component represented by the general formula [I] or [II] and having an intrinsic viscosity of 0.05-10 dl/g as measured at 135 °C in decalin and a softening temperature (TMA) not lower than 70 °C, and (B) a cycloolefin random copolymer containing an ethylene component, and a cycloolefin component represented by the general formula [I] or [II] and having an intrinsic viscosity of 0.01-5 dl/g as measured at 135 °C in decalin and a softening temperature (TMA) of below 70 °C, the weight ratio of said (A) component / (B) component ranging from 100/0.1 to 100/10.

The composition is particularly useful for mold-

ing an information recording base board.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 88 30 3919

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. CL.4)
A	EP-A-0 156 464 (MITSUI PETROCHEMICAL) * Abstract * ---	1	C 08 G 61/08 C 08 F 210/02 C 08 L 23/08 C 08 L 65/00
A	EP-A-0 203 799 (MITSUI PETROCHEMICAL) * Abstract * -----	1	
			TECHNICAL FIELDS SEARCHED (Int. CL.4)
			C 08 F C 08 G C 08 L
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 10-04-1990	Examiner GOOVAERTS R.E.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document	

EPO FORM 1503 (01.87) (P0401)